DATE: 27 January 2016

## **Product Identifier**

SRM Number: 2100b

**SRM Name:** Fracture Toughness of Ceramics

Under the U.S. Department of Labor, Occupational Safety and Health Administration (OSHA) 29 CFR 1910.1200, this Standard Reference Material (SRM) is NOT classified as a physical hazard or a health hazard, a simple asphyxiant, combustible dust, pyrophoric gas, or hazard not otherwise classified. There are no hazard pictograms, hazard statements or signal word associated with it. Safety Data Sheet information is not required. This document may be used in conjunction with your hazard communication program.

**Exemption:** 1910.1200 (c). This SRM is an Article, as the word is defined by OSHA, where *Article* means a manufactured item other than a fluid or particle: (i) which is formed to a specific shape or design during manufacture; (ii) which has end use function(s) dependent in whole or in part upon its shape or design during end use; and (iii) which under normal conditions of use does not release more than very small quantities, e.g., minute or trace amounts of a hazardous chemical (as determined under paragraph (d) of 1910.1200), and does not pose a physical hazard or health risk to employees.

**Description:** This SRM is intended for verification of fracture toughness testing procedures. This SRM may be used with any fracture toughness test method, but is optimized for beam bending testing configurations. A unit of SRM 2100b consists of a set of five hot-pressed silicon nitride flexure specimens cut from a single billet (plate) of material.

**Disposal:** SRM 2100b should be disposed of in accordance with local, state, and federal regulations.

**Transport Information:** This material is not regulated by the U.S. Department of Transportation (DOT) and/or International Air Transport Association (IATA).

**Disclaimer:** This document was prepared carefully, using current references. Users of this SRM should ensure that this document and the corresponding Certificate in their possession are current. This can be accomplished by contacting the SRM Program: telephone (301) 975-2200; fax (301) 948-3730; e-mail srmmsds@nist.gov; or via the Internet at http://www.nist.gov/srm.

SRM 2100b Page 1 of 1